

DINITROL 77 B

Corrosion Protection Wax Spray

Characteristics:

DINITROL 77 B is a long-term corrosion protection product. After drying, the product forms a light brown wax-like film. In light of its hardness, the product offers good protection against mechanical loads.

DINITROL 77 B is predominantly used as underbody protection in the vehicle industry. It is also used in shipbuilding and as temporary corrosion protection for tools and machines.

DINITROL 77 B is not harmful to vehicle lacquers and adheres well to practically all substrates.

Instructions for use:

Leave the spray can at room temperature (16 – 20°C). Before use, shake the can briefly. The surfaces to be treated, vehicle underbody, wheel housing, inside doors, etc. must be free from dust and grease. Spray product in an even cross coat at a distance of 20 – 30 cm.

Warning:

Product must not be applied to brake drums, brake discs, exhaust systems and drive shafts.

Technical properties:

Base:	wax mixture
Colour:	light brown / transparent
Film type:	hard – wax-like
Density / active agent 23°C:	0.735 g/cm ³
Solids content:	35,4%
Flash point / active agent:	29°C
Flash point / spray:	< -20
Recommended layer thickness:	200 µm
Recommended film thickness wet:	50 µm
Drying time:	approx. 30 min
Heat stability:	105°C
Removability:	Petroleum spirit
Propellant (aerosol):	Propane/butane
Storage aerosol:	cool and dry < 50°C
Hazard indication: R 12	highly flammable
Package:	500 ml

For all relevant safety advices please read the material safety data sheet or the packaging label.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH
Pyrmonter Str. 76
D-32676 Lügde
Telefon:
+49 (0) 52 81 / 9 82 98-0
Telefax:
+49 (0) 52 81 / 9 82 98-60
E-Mail:
service@dinol.com